

## Data sheet

31.10.2022

## Filter paper

Parameter*	Value*
Grade	MN 615
Basis weight	70 g/m <sup>2</sup>
Thickness	0.16 mm
Filtration speed	22 s
Surface	smooth
Ash content	0.1 %
Average retention capacity	4–12 µm

Characteristics / Application      Medium fast filtration, for general laboratory use

\*These data are typical values and must not be regarded as specification.



MACHEREY-NAGEL GmbH & Co. KG  
 Valenciennes Str. 11  
 52355 Düren · Germany  
[www.mn-net.com](http://www.mn-net.com)

DE Tel.: +49 24 21 969-0    info@mn-net.com  
 CH Tel.: +41 62 388 55 00    sales-ch@mn-net.com  
 FR Tel.: +33 388 68 22 68    sales-fr@mn-net.com  
 US Tel.: +1 888 321 62 24    sales-us@mn-net.com